Uniktryk Print 7PV2

Fuldfarvet mat tekstilprint · UFLEX7PV2

Producentens materialebillede; vejledende farve og finish.

DOKUMENTEREDE SYMBOLER

- **M** — Mat overflade
- **SOLV** — Solvent-blæk
- **ECO-S** — Eco-solvent-blæk
- **LATEX** — Latex-blæk

Materialets egne egenskaber: SOLV · ECO-S · LATEX · 60 °C maks. · OEKO-TEX oplyst

Sådan passer du på dit Uniktryk

01 Vent mindst 24 timer før første vask; en uge anbefales for bedre blækholdbarhed.

02 Vask på vrangen ved højst 60 °C, hvis tøjet tillader det. Ingen klorblegning, skyllemiddel eller tørretumbling.

03 Lufttør. Stryg på vrangen, aldrig direkte på trykket. Brug på Softshell er ikke godkendt; andre tekstiler skal prøves først.

Den mest skånsomme begrænsning på tøjets etiket eller i den konkrete produktkombination gælder. Kontakt os ved skader; undlad selv at varme eller lime.

Materiale, egenskaber og ansvarligt valg

PU-film fra vandbaseret emulsion uden DMF eller lignende opløsningsmidler. OEKO-TEX STANDARD 100 er oplyst for materialet. Printkompatibilitet er ikke det samme som HP Latex-certificering.

PET/polyesterliner. Ikke KRAFT- eller PE-liner.

M: Mat beskriver udseendet. Det betyder ikke, at folien tåler polering. SOLV: Kompatibel med solventbaseret blæk. Ikke en renseanvisning med opløsningsmiddel. ECO-S: Kompatibel med den angivne blæktype. Betegnelsen er ikke en miljøcertificering. LATEX: Blækkompatibilitet er ikke det samme som særskilt HP Latex-certificering.

Før produktion kontrollerer Uniktryk den præcise reference, underlag, materialekombination og monteringsmetode. Følg den konkrete pleje. Symboler er ikke en generel garanti eller tilladelse til andre anvendelser. Kilde: katalog 2026, trykt side 26, samt det vedlagte datablad.

Producentens CSR-temaer: Miljøpåvirkning · Etik og lokalsamfund · Ansvarlig innovation · Arbejdsvilkår.

Temaerne er virksomhedsindsatser, ikke fire produktcertifikater. Målet om 55 % lavere GHG-udledning i 2050 er producentens fremtidige mål, ikke dette produkts dokumenterede klimaaftryk. Kilde: katalog 2026, trykte sider 18-21.

Scan til den aktuelle vejledning

De følgende sider er producentens originale tekniske datablad. Produktkoder og kildeangivelser er bevaret, så materialet kan spores. Vejledningen begrænser ikke dine lovbestemte rettigheder.

UFLEX7PV2

WHITE

PRODUCT DESCRIPTION:

85-µm, adhesive-coated polyurethane film, made from a water-based emulsion, which is free of DMF or similar solvents. Opaque white, thin film, recommended for applications to cotton and polyester textiles (except Softshell). Especially adapted for the creation of letterings, logos or small images. Matt surface finish.

FILM FEATURES:

	(Indicative value)
• Thickness	**85 µm**

LINER:

- 105-µm polyester backing paper.

APPLICATION GUIDE FOR FLEX:

- Good adhesion to cotton and polyester.
- Do not use the UFLEX7PV2 film on Softshell fabrics.

For any other type of textile, carry out a test to check the resistance of the fabric to the press temperature and the compatibility of the UFLEX7PV2 film with the cloth.

- Print the image in positive mode.

Cutting and weeding
Cut and weed the image.
Minimum cutting size (unprinted areas or perfectly dry, printed areas): 0,6 cm (0.24 in.) (height of letters).

Prerequisites
It is preferable to apply the film to previously washed fabrics.

- Preheat press and textile prior to application.

Pressing temperature
140 °C (284 °F)

Pressing duration
15 seconds

In any case, always perform a preliminary trial so as to best adjust the pressing conditions before carrying out large series.

Pressing strength
high pressure

Carefully remove the transfer tape while the film is still: **hot**

- Place parchment paper on the graphic's surface.

Repressing temperature
140 °C (284 °F)

Repressing duration
5 seconds

Rest time before washing
After pressing, wait for at least 24 hours before washing the garment. For better ink durability, it is preferable to wait for one week before carrying out the first washing.

Washing temperature
with a maximum of 60 °C (140 °F)

Washing conditions
Use laundry products without chlorine bleach.

Drying conditions
Tumble drying is prohibited.

Ironing conditions
Iron your garment inside out.

OPERATING RECOMMENDATIONS:

- For each new application of UFLEX7PV2 films to Lycra® based fabrics, verify the compatibility of the UFLEX7PV2 film with this material by producing a garment corresponding to the end product.

Due to the high variability of these substrates, HEXIS decline all responsibility related to the behaviour of the end product.

- The use of softeners is not recommended since it can cause an alteration of the flex film adhesion to the fabric.
- For more information on the application method of the UFLEX7PV2 film, please refer to the PRINTFLEX Application Guide available under the «Professionals» heading, in the «Films for textile" category on our website www.hexis-graphics.com.

Uniktryk 2026 / rev. 5 - originalt producentbilag, rettigheder respekteres

STORAGE:

Storage period before use
1 year

Storage temperature
+15 °C to +25 °C (+59 °F to +77 °F)

Relative humidity during storage
with relative humidity between 30 % and 70 %

Storage method before use
in its unopened original packaging

LABELLING PRODUCT:

Oeko-Tex® Standard 100 label

OEKO TEX®
STANDARD 100
CQ 1126/1
IFTH

NOTES:

Due to the great variety of substrates and the growing number of new applications, the installer must check the suitability of the medium for each application. All of the published information is based on measurements regularly performed in the laboratory. The published information does not however constitute a binding guarantee. The seller cannot be held liable for indirectly related damages and assumes no liability for claims that are higher than the replacement value of the purchased product. All specifications are subject to potential changes without prior notice. Our specifications are automatically updated on our website www.hexis-graphics.com.

Unik Tryk
Folie · Print · Tryk · Klistermærker · Design

Uniktryk 2026 / rev. 5 - originalt producentbilag, rettigheder respekteres